

# RANCO INDUSTRIES, INC

## **SPEC SHEET**

#### **Product Data Sheet**

Product Name: Diamond Plate Runner

Surface Configuration: Top – Deckplate Pattern

Bottom - Knurled for slip-resistance

Thickness: 5/32" Minimum

Chemical Resistance: Excellent chemical resistance to many commercial and industrial

chemicals. Please call for specific recommendations.

### **Physical Properties**

Characteristics	Performance	Test Method	
Tensile Strength	1250 psi	ASTM-D-412	
Elongation	250%	ASTM-D-412	
Moisture Absorbtion	.08%	ASTM-D-412	
Coefficient of Friction	.68 Dry / .17 Wet	ASTM-F-1677	
Tohar Abrasian	10/ lost at 1 000 avalos	Fod Ctd 102 Modifi	

Taber Abrasion 1% lost at 1,000 cycles Fed. Std. 193 Modified

Flammability Self-Extinguishing MVSS 302

#### **Chemical Resistance**

Chemical	Ranking	Chemical	Ranking
Butyl Alcohol	Good	Nitric Acid (dilute)	Excellent
Carbon Tetrachloride	Good	Nitric Acid 30%	Excellent
Chromic Acid (dilute)	Great	Potassium Permanganate(dilu	te) Good
Gasoline	Great	Sodium Perborate	Good
Hydrogen Peroxide (dilute)	Good	Sodium Hydroxide	Good
Most Acids	Good	Sulfuric Acid (dilute)	Good
Most alkalis	Good	Water	Excellent